

CLIENT: Sabic Innovative Plastics US LLC  
1 Lexan Lane  
Mount Vernon, IL 47620  
  
Attn: Constantin Donea

<http://www.sundancesupply.com>

Test Report No:	654:0281839-13	Date:	November 6, 2009
-----------------	----------------	-------	------------------

SUBJECT: Testing to ASTM D 635

SAMPLE ID: Sample identified as “**25mm – with ribbing**” was received from the client on 9/24/09 in good condition. The sample was described by the manufacturer of containing the following items:

- **Sample: Lexan Thermoclear 25mm Sheet, commercialized under the grade names LTP5X25, 2XP5X25, LPD5X25, LED5X25, LXE5X25, LXD5X25**

TEST REQUESTED: The submitted sample was tested for Rate of Burning and/or extent of time of burning of plastics in a horizontal position in accordance to procedures outlined in ASTM D 635-06.

PREPARATION: The sample material was submitted in ten pieces, 13.5mm x 25mm x 127mm

TEST DATE: 11/6/09

RESULTS: Results can be found on the following pages and apply only to the sample tested.

CLASSIFICATION: CC1

SIGNED FOR AND ON BEHALF OF  
SGS U.S. TESTING COMPANY INC.

KSM



Cody Allen  
Engineering Technician



For: J. Brian McDonald  
Fire Technology Department Manager

Page 1 of 2

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only.



**SAMPLE:** 25mm – with ribbing      **TEST DATE:** 11/6/09      **Equipment Number:** 061-10  
 Conditioning Treatment: 69.8 – 77.0 °F      Relative Humidity: 50 ± 5% for 48 hours  
 Temperature and Humidity at time of Testing: 71.0°F      Relative Humidity: 52%

**DATA:**

<u>Specimen Number</u>	<u>Dimensions (mm)</u>	<u>Burning Time (Sec)</u>	<u>Burned Length (mm)</u>	<u>Burn Rate (mm/min)</u>
1	127 x 13.5 x 25	_*	_*	_*
2	127 x 13.5 x 25	_*	_*	_*
3	127 x 13.5 x 25	_*	_*	_*
4	127 x 13.5 x 25	_*	_*	_*
5	127 x 13.5 x 25	_*	_*	_*
6	127 x 13.5 x 25	10	7.25	.725
7	127 x 13.5 x 25	_*	_*	_*
8	127 x 13.5 x 25	_*	_*	_*
9	127 x 13.5 x 25	_*	_*	_*
10	127 x 13.5 x 25	3	7	2.334
<b>AVERAGE</b>	<b>127 x 13.5 x 25</b>	<b>1.3</b>	<b>1.425</b>	<b>.55</b>

\* - Specimen ceases to burn before reaching the 25mm gauge mark

**Observations:** Specimens stopped burning once the flame was removed.

**NOTES:**

**Class CC1:** "Plastic materials that have a burning extent of 1 inch (25.4mm) or less where tested at a normal thickness of 0.060 inch (1.5mm), or in the thickness intended for use, in accordance with ASTM D 635"

**Class CC2:** "Plastic materials that have a burning rate of 2.5 inches (1.06mm) or less where tested at a normal thickness of 0.060 inch (1.5mm), or in the thickness intended for use, in accordance with ASTM D 635"

**CBC:** Cannot Be Classified. This description is for any test results that do not meet CC1 or CC2 criteria.

The CC rating is in accordance with the International Building Code-2006.

\*\*\*\*\*

**End of Report**

Page 2 of 2

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at [www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm) and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at [www.sgs.com/terms\\_e-document.htm](http://www.sgs.com/terms_e-document.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 90 days only.